



Our Ref: 27/02346B/08/11

Your Ref:

Order No: 38083

14 September 2011

Page 1 of 3

Client: ISINAC ACOUSTIC WORLD SL  
c / Lopez de Neira 3  
36203 - Vigo - Spain

Job Title: **Fire Test on One Sample of Fabric**

Material Received: 31 August 2011

Description of Sample: One sample of fabric, referenced: ILUCS

Brief: Fire Technology Services were requested to carry out a fire test on the sample supplied to BS 476 Part 7.

UKAS Accreditation:

Our Laboratories are UKAS accredited. However, it should be noted that tests marked \* are not UKAS accredited in this report. They are not included in the UKAS Accreditation Schedule for our laboratory, either due to the work not conforming fully to the standard (e.g. reduced number of specimens) or to it being outside the scope of our accreditation, or subcontracted.

Uncertainty:

An estimation of uncertainty of measurement has not been taken into account when making a judgement to any pass/fail criteria.





**FIRE TESTS ACCORDING TO BS 476:PART 7:1987 (AS AMENDED)**  
(Method for classification of the surface spread of flame of products)

**Date of Test: 14/09/11**

**Conditioning**

The sample was conditioned to constant mass at a temperature of  $23 \pm 2^\circ\text{C}$  and a relative humidity of  $50 \pm 10\%$  and maintained in this condition until required for testing

**Procedure**

The test was carried out in accordance with BS 476: Part 7: 1987. The sponsor sampled the material and the specimens were cut from the sample to the dimensions set out in the standard by the sponsor. The specimens were tested stuck down onto 12mm calcium silicate board using Murabond Heavy Adhesive.

The following were recorded:-

- the time at which the flame front crosses each vertical reference line;
- the maximum extent of flame spread during the first 1.5 min from the start of the test;
- the maximum extent of flame spread during the whole test i.e. 10 min or less (if applicable)
- the time (and distance) at which maximum flame spread is reached.

The flame spread at 1.5min and the final flame spread results were compared with the standard class limits and a classification was assigned.

**Requirements**

The class limits for flamespread, detailed in BS 476:Part 7: are set out below.

	Flame spread at 1.5 min (mm)	Final flame spread (mm)
Class 1	165 (+ 25)	165 (+ 25)
Class 2	215 (+ 25)	455 (+ 45)
Class 3	265 (+ 25)	710 (+ 75)
Class 4	Exceeding Class 3 limits.	

A definitive classification is based on a sample of six specimens and the figure in brackets gives the tolerance by which only one specimen in six may exceed the class limit assigned.



## Results

The test results relate only to the behaviour of the test specimens of the product under the particular conditions of test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.


Time for flame spread to reach (s) (mm)					Flame spread at 1.5 min (mm)	Maximum flame spread (mm)	Time to reach maximum flame spread (s)
165	215	265	455	710			
--	--	--	--	--	60	60	60
--	--	--	--	--	60	60	60
--	--	--	--	--	60	60	60
--	--	--	--	--	60	60	60
--	--	--	--	--	60	60	60
--	--	--	--	--	60	60	60

The results indicate that the sample met the performance requirements of Class 1.


## Observations

--

The information contained on page no's 1/3 of this certificate is hereby certified to be a correct statement of the tests and investigations carried out by FTS on the materials referred to.

Signed.....  Date 14 September 2011

Mrs B Marsden  
Fire Technician

Reported By.....  Date 14 September 2011

P Doherty  
Operational Head